

Maintenance

The proposed Tefcote Standard Specification 2, Topcoat P3000HRX / N4000HRX is a flexible performance decorative finish with good mechanical and chemical resistance. The coating can withstand all ordinary cleaning materials for walls.

Schedule, short term

To maintain the surface finish, it is advised that all surfaces coated with Tefcote Surface Systems are cleaned on a regular basis.

- Use household type detergents for wipe down on a regular basis, i.e. Lever Industrial Ltd. Quatdet, Foamclean or similar. Avoid abrasives and caustic cleaners such as cream cleaners and oven cleaners etc. and cleaners with pH value of more than 10.
- The coating will withstand regular cleaning.

Schedule, long term

For long term maintenance, the Topcoat P3000HRX / N4000HRX Specification can be over coated subject to light glass paper abrasion, and will reproduce a smooth homogeneous surface:

- Application by airless spray, brush or roller
- The material is waterborne and non hazardous
- Under ambient conditions, the coating is touch dry within 4-6 hours and hard dry after 24 hours
- Full properties in 7 days

If in doubt, contact: office@tefcote.co.uk